



SoundLevel™

Next Generation Sound Reducing & Self-Leveling Liquid Underlayment

SPECIFICATION SHEET

SoundLevel™ Next Generation Sound Reducing Liquid Underlayment Patch and

SoundLevel™ Next Generation Sound Reducing Liquid Underlayment Patch and Leveler is designed for all floating floor systems (vinyl tile/plank, laminate, and wood) to reduce sound transmission (up to IIC 71 and STC 67). SoundLevel™ also controls moisture levels, patches up to 1/8" cracks, levels substrate unevenness, and enhances thermal insulating properties of the floor. It is an excellent replacement for rolled sound reducing membranes with its easy installation, one-hour set-up time and when fully cured it is a sealed, leveled, and flat membrane. Requirements for installing underlayment are simple; it is unaffected by concrete slab alkalinity, can be installed on porous or non-porous surfaces, and has extremely low permeability ratings. As the product cures it uses its formulated cross-linking modified silane polymer-base to build a tenacious but elastic resilient membrane.

SoundLevel™ is free of solvents, hazardous chemicals (per OSHA Regulation CFR 1910.1200), water, and isocyanates. This product is a one component, 100% solids, non-flammable and low odor liquid underlayment with negligible VOC content that meets federal, state, and local governmental indoor air quality regulations; achieving the coveted UL's GREENGUARD Certification.

USE OVER:

SoundLevel™ may be used over APA grade underlayment plywood, flooring grade particleboard, OSB, cork underlayment, existing well bonded non-cushioned resilient flooring, terrazzo, cementitious and anhydrite screeds, concrete, and radiant heated subfloors where surface temperatures do not exceed 85°F (30°C). Install above, on, or below grade, in the absence of excessive moisture. While this barrier is waterproof when cured, the installation still must be protected from excessive moisture. Moisture levels of concrete must be below 10 lb/1000 sq. ft./24 hr per ASTM F-1869 test method & relative humidity (RH) 90% per ASTM F-2170. When installing SoundLevel™ use a 1/16" x 3/32" saw tooth trowel, or 3/16" x 5/32" saw tooth trowel for patching or self-leveling, for all installations. The moisture content must be within the flooring manufacturer's guidelines for allowable levels of moisture.

SUBSTRATE PREPARATION:

Substrate must be sound, smooth, clean, level, dry, and free of dust, dirt, grease, oil, paint, curing compounds, incompatible sealers, fire retardant chemicals, release agents, or any other foreign substance that might interfere with a good bond. Subfloor must be smooth and fully adhered. Depending on the type and condition of the subfloor, mechanical treatment of the subfloor such as mechanical brushing, grinding with coarse sand paper, milling or ball blasting may be required. It is the sole responsibility of the installer/contractor to ensure that the concrete surface is properly prepared prior to installation.

INSTALLATION:

SoundLevel, the floor covering and areas to receive flooring must be maintained at a temperature of 65° - 95°F (18° - 35°C) and at a relative humidity of 30% - 60% for 72 hours before, during, and after installation. Follow the flooring manufacturer's guidelines regarding site conditions, layout, and installation.

Apply SoundLevel with the recommended trowel and allow to dry and cure for approximately one hour; however, SoundLevel underlayment must be dried and cured throughout the film thickness before installing the floating floor system. The drying time will vary with ambient job site conditions. Always follow the flooring manufacturer's installation guidelines for their floating floor systems.

NOTE: When using the 3/16" x 5/32" saw tooth trowel for patching and self-leveling, SoundLevel™ may require more cure time. Damp mopping the floor prior to application can speed up cure time. Follow all other instructions for floor preparation.

TROWEL RECOMMENDATIONS

TROWEL RECOMMENDATIONS

For sound reducing underlayment, moisture barrier, and filling cracks up to 1/8" wide:

1/16"x3/32" saw tooth

(1.6mm x 2.4 mm)

Estimated Up to 100 sq. ft./gal

2.5 sq. meters/liter

For sound reducing underlayment, moisture barrier, filling cracks up to 1/8" wide, patching and leveling uneven floors up to 1/8" depth in 10 feet:

3/16"x5/32" saw tooth

(4.8mm x 4.0mm)

Estimated Up to 60 sq. ft./gal

1.5 sq. meters/liter

NOTE: Liquid underlayment coverage is approximate and will vary depending on the porosity and roughness of subfloor, angle at which the trowel is held, temperature of the liquid underlayment and subfloor, and the skill of the installer applying the liquid underlayment. The liquid underlayment coverage will be improved by priming the subfloor to reduce absorption of the liquid underlayment into the subfloor. The underlayment coverage will be significantly lower over subfloors not properly prepared according to established industry guidelines.

SOUND REDUCTION SYSTEM

| Floor System | IIC Rating | STC Rating |
|-----------------------------------------------------|------------|------------|
| SoundLevel Underlayment | 69 | 66 |
| SoundLevel Underlayment with Vinyl, Wood & Laminate | 69-71 | 66-67 |

OTHER PROPERTIES:

Appearance: White, smooth, creamy, easy to trowel.

Working time: 30 minutes depending on temperature and humidity.

Shelf life: One year in unopened container at 70° F (21°C).

Other features: Provides sound reduction, moisture inhibition, crack isolation, and enhances thermal insulation. VOC compliant, nonflammable, and freeze/thaw stable to 10° F (-12° C). Made with anti-microbial agents that will provide its dry film with protection from fungal growth. This protection is determined using the ASTM G21 test method.

Clean Up: Clean up with warm water when wet, Taylor Touchdown #9 Adhesive Remover/Stripper.

STORAGE: This product should be stored at temperatures between 50° and 90° F (15°- 32° C). Storage conditions outside this range may cause product viscosity to increase.

CAUTION:

DO NOT take internally. If swallowed, DO NOT induce vomiting.

Call a physician immediately. KEEP OUT OF REACH OF CHILDREN.

Warranty Information: This product is manufactured according to exacting quality control standards and is warranted to be free from manufacturing defects. Defective material called to our attention within one year of manufacture will be replaced. No guarantee, expressed or implied, is made regarding the performance of this product since the manner and conditions of application are beyond our control. For complete warranty information, call Technical Services at 800-868-4583 ext 2221, visit us on the web at www.wftaylor.com or e-mail us at tech@wftaylor.com.

This product is packaged with 100% post-industrial reground plastic.

© W. F. Taylor Co., Inc. Dalton GA. All Rights Reserved. Visit wftaylor.com
 Technical Service 800.868.4583 Ext: 221 or e-mail us at tech@wftaylor.com
 Customer Service 866.818.7434